



US009054295B2

(12) **United States Patent**  
**Gotti et al.**

(10) **Patent No.:** **US 9,054,295 B2**  
(45) **Date of Patent:** **Jun. 9, 2015**

(54) **PHASE CHANGE MEMORY CELLS INCLUDING NITROGENATED CARBON MATERIALS, METHODS OF FORMING THE SAME, AND PHASE CHANGE MEMORY DEVICES INCLUDING NITROGENATED CARBON MATERIALS**

(75) Inventors: **Andrea Gotti**, Pozzo D'adda (IT); **Luca Fumagalli**, Milan (IT)

(73) Assignee: **Micron Technology, Inc.**, Boise, ID (US)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 671 days.

(21) Appl. No.: **13/215,706**

(22) Filed: **Aug. 23, 2011**

(65) **Prior Publication Data**  
US 2013/0048935 A1 Feb. 28, 2013

(51) **Int. Cl.**  
**H01L 21/8239** (2006.01)  
**H01L 27/24** (2006.01)  
**H01L 45/00** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **H01L 45/06** (2013.01); **H01L 45/1253** (2013.01); **H01L 45/143** (2013.01); **H01L 45/144** (2013.01); **H01L 27/2463** (2013.01)

(58) **Field of Classification Search**  
CPC ..... H01L 45/06; H01L 27/249; H01L 45/144; H01L 45/04; H01L 45/12; H01L 45/1253; H01L 45/143; H01L 31/0324; H01L 21/02417; H01L 27/2463; G11C 13/0002-13/0004

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,536,947	A *	7/1996	Klersy et al.	257/3
5,616,374	A	4/1997	Sho	
6,800,504	B2	10/2004	Li et al.	
7,115,927	B2	10/2006	Hideki et al.	
7,667,218	B2	2/2010	Yamamoto et al.	
7,791,932	B2	9/2010	Kuh et al.	
7,858,152	B2 *	12/2010	Ovshinsky et al.	427/331
7,884,347	B2 *	2/2011	Yoon et al.	257/4
7,943,922	B2 *	5/2011	Fournier	257/4
2006/0278900	A1 *	12/2006	Chang et al.	257/248
2007/0221906	A1	9/2007	Hideki et al.	
2007/0284635	A1 *	12/2007	Fournier	257/295
2008/0075843	A1	3/2008	Kuh et al.	
2008/0145702	A1 *	6/2008	Shin et al.	428/698
2009/0029031	A1 *	1/2009	Lowrey	427/58
2009/0146130	A1 *	6/2009	Fournier	257/4
2009/0179186	A1 *	7/2009	Arnold et al.	257/2
2009/0180314	A1 *	7/2009	Liu	365/163
2009/0275198	A1 *	11/2009	Kamepalli et al.	438/659
2010/0019216	A1 *	1/2010	Park et al.	257/2
2010/0084625	A1	4/2010	Wicker et al.	
2010/0096609	A1 *	4/2010	Kim et al.	257/2
2011/0024713	A1 *	2/2011	Kamata et al.	257/2
2011/0149645	A1 *	6/2011	Liu	365/163
2013/0017663	A1 *	1/2013	Park et al.	438/382
2013/0078475	A1 *	3/2013	Zheng	428/457
2014/0239245	A1 *	8/2014	Lengade et al.	257/4


\* cited by examiner


*Primary Examiner* — William F Kraig  
*Assistant Examiner* — Maliheh Malek  
(74) *Attorney, Agent, or Firm* — TraskBritt

(57) **ABSTRACT**


A phase change memory cell comprising a first chalcogenide compound on a first electrode, a first nitrogenated carbon material directly on the first chalcogenide compound, a second chalcogenide compound directly on the first nitrogenated carbon material, and a second nitrogenated carbon material directly on the second chalcogenide compound and directly on a second electrode. Other phase change memory cells are described. A method of forming a phase change memory cell and a phase change memory device are also described.

**23 Claims, 9 Drawing Sheets**





**FIG. 1**



**FIG. 2**




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 7C






FIG. 7D




FIG. 7E




FIG. 8

**PHASE CHANGE MEMORY CELLS  
INCLUDING NITROGENATED CARBON  
MATERIALS, METHODS OF FORMING THE  
SAME, AND PHASE CHANGE MEMORY  
DEVICES INCLUDING NITROGENATED  
CARBON MATERIALS**

TECHNICAL FIELD

The present disclosure relates generally to phase change memory cells. More specifically, embodiments of the present disclosure relate to phase change memory cells including nitrogenated carbon materials, methods of forming such phase change memory cells, and phase change memory devices including such nitrogenated carbon materials.

BACKGROUND

Non-volatile memory devices are an important element of integrated circuits due to their ability to maintain data absent a power supply. Phase change materials have been investigated for use in non-volatile memory cells. Phase change memory cells include phase change materials, such as chalcogenide compounds, which are capable of stably transitioning between physical states (e.g., amorphous, semi-amorphous, and crystalline states). Each physical state exhibits a particular resistance that may be used to distinguish logic values of the memory cell.

A conventional phase change memory cell includes a layer of phase change material between a first electrode and a second electrode. A portion of the phase change memory cell is set to a particular resistance state according to an amount of current applied by the first electrode and the second electrode. To obtain an amorphous state, a high current pulse is applied to the phase change material for a short period of time to melt a portion of the phase change material. The current is removed and the phase change memory cell cools rapidly to below the glass transition temperature of the phase change material. To obtain a crystalline state, a lower current pulse is applied to the phase change material for a longer period of time to heat the phase change material to below its melting point, causing the amorphous state to re-crystallize to a crystalline state that remains after the current is removed.

Conventional phase change memory cells typically also include an isolation element. Within a conventional phase change memory device, a plurality of phase change memory cells are positioned between a plurality of access lines (e.g., word lines) and a plurality of digit lines (e.g., bit lines). Each access line is connected to a row of phase change memory cells and each digit line is connected to a column of phase change memory cells. A single phase change memory cell is selected for reading or writing by applying a voltage between the access line and the digit line to which the single phase change memory cell is connected. Including an isolation element in the phase change memory cell impairs or, ideally, prevents residual voltages from affecting the physical state of non-selected phase change memory cells. Threshold switching materials are currently considered favorable isolation elements. One threshold switching material is a chalcogenide compound having an OFF state that is relatively resistive (i.e., precluding current leaks) and an ON state that is relatively conductive. The ON state of the threshold switching material is enabled when a voltage across the threshold switching material is greater than a critical threshold value of the threshold switching material.

Disadvantageously, conventional phase change memory devices require large amounts of energy to generate the heat

to produce a detectable resistance change in the plurality of phase change memory cells. The electrodes used to generate such heat are often insufficiently resistive. Conventional electrodes also frequently exhibit poor resistivity stability over varied temperatures and have a tendency to be chemically reactive with the phase change material of the phase change memory cell, which can result in limited memory cell lifespan, performance degradation, and even delamination of the phase change material. Additionally, conventional electrode materials do not exhibit good adhesion with phase change materials. Further, conventional electrodes often have textured, uneven, or rough surfaces that can protrude through a portion of the phase change material and negatively affect memory characteristics.

There remains a need for a phase change memory cell and a phase change memory device providing the benefits of a threshold switching material without one or more of the foregoing disadvantages of conventional phase change memory cells and devices.

BRIEF DESCRIPTION OF THE SEVERAL  
VIEWS OF THE DRAWINGS

FIG. 1 is a cross-sectional view of a phase change memory cell, in accordance with an embodiment of the disclosure.

FIG. 2 is a cross-sectional view of another phase change memory cell, in accordance with an embodiment of the disclosure.

FIG. 3 is a cross-sectional view of yet another phase change memory cell, in accordance with yet another embodiment of the disclosure.

FIG. 4 is a cross-sectional view of still yet another phase change memory cell, in accordance with yet another embodiment of the disclosure.

FIG. 5 is a perspective view of a phase change memory cell array including a plurality of phase change memory cells of the present disclosure.

FIG. 6 is a cross-sectional view of a phase change memory device in accordance with an embodiment of the present disclosure.

FIGS. 7A-7E are cross-sectional views illustrating different process stages and structures for a method of forming the phase change memory device of FIG. 6.

FIG. 8 is a graphical representation of the resistivity stability of a nitrogenated carbon material as a function of temperature as described in Example 1.

DETAILED DESCRIPTION

Phase change memory cells, methods of forming such phase change memory cells, and phase change memory devices including the phase change memory cells are disclosed. The phase change memory cell includes at least one nitrogenated carbon material, which may function as at least one of an electrode and an adhesion material. The nitrogenated carbon material may be a crystalline material including carbon atoms and nitrogen atoms. The phase change memory cells utilizing the nitrogenated carbon materials may exhibit increased adhesion strength, improved surface smoothness, higher resistivity, improved resistivity stability with temperature change, reduced hysteresis and degradation, and reduced power consumption requirements relative to conventional phase change memory cells.

The following description provides specific details, such as material types, material thicknesses, and processing conditions in order to provide a thorough description of embodiments of the present disclosure. However, a person of ordi-

nary skill in the art will understand that the embodiments of the present disclosure may be practiced without employing these specific details. Indeed, the embodiments of the present disclosure may be practiced in conjunction with conventional fabrication techniques employed in the industry. In addition, the description provided herein does not form a complete process flow for forming a phase change memory cell, and each of the phase change memory cells and phase change memory devices described below do not form a complete semiconductor device. Only those process acts and structures necessary to understand the embodiments of the present disclosure are described in detail below.

In the following description, reference is made to the accompanying drawings, which form a part hereof, and in which is shown, by way of illustration, specific embodiments in which the disclosure may be practiced. These embodiments are described in sufficient detail to enable a person of ordinary skill in the art to practice the disclosure. However, other embodiments may be utilized, and structural, logical, and electrical changes may be made without departing from the scope of the disclosure. The illustrations presented herein are not meant to be actual views of any particular phase change memory cell, phase change memory array, or phase change memory device but are merely idealized representations that are employed to describe embodiments of the present disclosure. The drawings presented herein are not necessarily drawn to scale. Additionally, elements common between drawings may retain the same numerical designation.

As used herein, while the terms “first,” “second,” “third,” etc., may describe various elements, components, regions, layers, and/or sections, none of which are limited by these terms. These terms are used only to distinguish one element, component, region, material, layer, or section from another element, component, region, material, layer, or section. Thus, “a first element,” “a first component,” “a first region,” “a first material,” “a first layer,” or “a first section” discussed below could be termed a second element, a second component, a second region, a second material, a second layer, or second section without departing from the teachings herein.

As used herein, reference to an element as being “on” another element means and includes the element being directly on top of, adjacent to, underneath, or in direct contact with the other element. It also includes the element being indirectly on top of, adjacent to, underneath, or near the other element, with at least one other element present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

One embodiment of the present disclosure will now be described with reference to FIG. 1, which illustrates a phase change memory cell **100** including an optional first nitrogenated carbon material **104**, a phase change material **106**, a second nitrogenated carbon material **108**, a threshold switching material **110**, and a third nitrogenated carbon material **112**. The phase change memory cell **100** may be coupled to a first electrode **102** and a second electrode **114**. As shown in FIG. 1, the first nitrogenated carbon material **104** may, optionally, be formed on the first electrode **102**, the phase change material **106** may be formed on the first nitrogenated carbon material **104** (if present), the second nitrogenated carbon material **108** may be formed on the phase change material **106**, the threshold switching material **110** may be formed on the second nitrogenated carbon material **108**, the third nitrogenated carbon material **112** may be formed on the

threshold switching material **110**, and the second electrode **114** may be formed on the third nitrogenated carbon material **112**.

The first electrode **102** may include any suitable conductive material including, but not limited to, a metal, a metal alloy, a conductive metal oxide, or combinations thereof. For example, the first electrode **102** may be formed from tungsten (W), tungsten nitride (WN), nickel (Ni), tantalum nitride (TaN), platinum (Pt), gold (Au), titanium nitride (TiN), titanium silicon nitride (TiSiN), titanium aluminum nitride (TiAlN), molybdenum nitride (MoN), or a combination thereof. In at least some embodiments, the first electrode **102** is formed from W. The first electrode **102** may be formed in, on, or over a substrate (not shown) using conventional techniques, such as a physical vapor deposition (“PVD”) technique, a chemical vapor deposition (“CVD”) technique, or an atomic layer deposition (“ALD”) technique. PVD includes, but is not limited to, sputtering, evaporation, or ionized PVD. Such deposition techniques are known in the art and, therefore, are not described in detail herein. The substrate may be a base material or construction upon which additional materials are formed. The substrate may be a semiconductor substrate, a base semiconductor layer on a supporting structure, a metal electrode, or a semiconductor substrate having one or more layers, structures or regions formed thereon. The substrate may be a conventional silicon substrate or other bulk substrate including a layer of semiconductive material. The bulk substrate may include, but is not limited to, silicon, silicon-on-insulator (“SOI”), silicon-on-sapphire (“SOS”), epitaxial silicon on a base semiconductor foundation, or another semiconductor or optoelectrical material, such as silicon-germanium, germanium, gallium arsenide, or indium phosphide. The substrate may be doped or undoped.

The first nitrogenated carbon material **104**, if present, may be a non-stoichiometric compound including carbon (C) atoms and nitrogen (N) atoms. As used herein, the term “non-stoichiometric compound” means and includes a chemical compound with an elemental composition that cannot be represented by a ratio of well-defined natural numbers and is in violation of the law of definite and multiple proportions. The first nitrogenated carbon material **104** may function as an electrode configured to conduct current to the phase change material **106**. The first nitrogenated carbon material **104** may include a nitrogen content ranging from about 0.10 atomic percent nitrogen to about 20 atomic percent nitrogen, such as from about 0.5 atomic percent nitrogen to about 10 atomic percent nitrogen. The amount of carbon in the first nitrogenated carbon material **104** may be greater than the amount of nitrogen in the first nitrogenated carbon material **104**. By way of non-limiting example, the first nitrogenated carbon material **104** may have an atomic percentage of carbon greater than or equal to about 80 percent and an atomic percentage of nitrogen less than or equal to about 20 percent, such as greater than or equal to about 90 atomic percent carbon and less than or equal to about 10 atomic percent nitrogen, greater than or equal to about 95 atomic percent carbon and less than or equal to about 5 atomic percent nitrogen, greater than or equal to about 97 atomic percent carbon and less than or equal to about 3 atomic percent nitrogen, or greater than or equal to about 99 atomic percent carbon and less than or equal to about 1 atomic percent nitrogen. The first nitrogenated carbon material **104**, if present, may include an atomic percentage of nitrogen within a range of from about 0.10 atomic percent nitrogen to about 20 atomic percent nitrogen, such as from about 0.5 atomic percent nitrogen to about 10 atomic percent nitrogen. In at least some embodiments, the first nitrogenated carbon material **104** has an atomic percentage of carbon of about 95

percent and an atomic percentage of nitrogen of about 5 percent. The nitrogen content of the first nitrogenated carbon material **104** may enable the first nitrogenated carbon material **104** to have increased resistivity and increased resistivity stability with temperature variation as compared to conventional electrodes, such as carbon electrodes.

The first nitrogenated carbon material **104**, if present, may have a uniform nitrogen concentration profile. As used herein, the term “uniform nitrogen concentration profile” means and includes a concentration profile of nitrogen that does not vary by more than about 0.5 percent of an average nitrogen concentration for a thickness of a region of the material. Alternatively, the first nitrogenated carbon material **104** may have a non-uniform nitrogen concentration profile. If the first nitrogenated carbon material **104** has a non-uniform nitrogen concentration profile, a nitrogen concentration may vary stepwise or may vary continuously. As used herein, the term “vary stepwise” means and includes a concentration profile where a nitrogen concentration may change abruptly within a thickness of a region of the material. As used herein, the term “vary continuously” means and includes a concentration profile where a nitrogen concentration may change progressively (e.g., linearly or parabolically) throughout a thickness of a region of the material. The non-uniform concentration profile may simultaneously provide a thickness of a region of the material with advantageous thermal insulation properties and advantageous electrical resistivity properties. The non-uniform concentration profile may be substantially undetectable by visual detection, but may be detectable by conventional spectroscopy or spectrometry techniques.

The thickness of the first nitrogenated carbon material **104** may be selected at least partially based on material characteristics of one or more other components of the phase change memory cell **100** (e.g., the phase change material **106**, the second nitrogenated carbon material **108**, the threshold switching material **110**). For example, the thickness of the first nitrogenated carbon material **104** may enable a threshold voltage of the first nitrogenated carbon material **104** (e.g., a voltage at which the first nitrogenated carbon material **104** functions as a low resistance conductor) to be substantially close to a threshold voltage of the threshold switching material **110** (described below). The thickness of the first nitrogenated carbon material **104** may be within a range of from about 100 Å to about 2000 Å, such as from about 300 Å to about 1500 Å. In at least some embodiments, the thickness of the first nitrogenated carbon material **104** is about 1000 Å.

The first nitrogenated carbon material **104** may be formed on the first electrode **102** by conventional techniques including, but not limited to, PVD, CVD, or ALD. In one embodiment, the first nitrogenated carbon material **104** is formed by PVD, so that the first nitrogenated carbon material **104** has high film quality, as well as high thermal compatibility with the phase change material **106**. By way of non-limiting example, a carbon source, such as graphite, may be provided in a deposition chamber (not shown), such as a PVD chamber, that is configured to receive nitrogen gas at a flow rate of from about 0.1 standard cubic centimeters per minute (scm) to about 50 scm, and further configured to generate a plasma including a noble gas element (e.g., helium, neon, argon, krypton, xenon, or radon). In at least one embodiment, the plasma includes argon. Conditions, such as temperature and pressure, for generating and maintaining the plasma in the chamber may be conventional and, therefore, are not described in detail herein. As the carbon source is bombarded with the plasma, carbon atoms of the carbon source are sputtered from a surface of the carbon source and form on a surface of the first electrode **102**. Nitrogen atoms from the

nitrogen gas may covalently bond to the carbon atoms on the first electrode **102**, forming a coating of the first nitrogenated carbon material **104** on the surface of the first electrode **102**. The nitrogen content of the first nitrogenated carbon material **104** may depend on the flow rate of the nitrogen gas into the chamber. The greater the flow rate of the nitrogen gas into the PVD chamber, the greater the atomic percentage of nitrogen incorporated into the first nitrogenated carbon material **104**. If a non-uniform nitrogen concentration profile is desired, the flow rate of the nitrogen gas into the chamber may be increased or decreased in a stepwise manner or a continuous manner during the deposition process. A desired thickness of the first nitrogenated carbon material **104** may be achieved by controlling a deposition time and an amount of power used. Suitable PVD chambers are commercially available including, but not limited to, an Entron EX300 RF sputtering chamber, which is available from Ulvac Technologies, Inc. (Methuen, Mass.).

The phase change material **106** may be any known material capable of being electrically switched or changed (i.e., configured to reversibly electrically switch or change) between a first phase and a second phase, where the first phase and the second phase differ in at least one detectable (e.g., measurable) property (e.g., electrical resistivity, electrical conductivity, optical transmissivity, optical absorption, optical refraction, optical reflectivity, morphology, surface topography, relative degree of order, relative degree of disorder, or combinations thereof). For example, applying a high current pulse to a crystalline (i.e., a relatively more ordered structure or arrangement of atoms) state of the phase change material **106** for a short time may cause the phase change material **106** to switch or change from the crystalline state having a relatively low resistivity to an amorphous (i.e., a relatively less ordered structure or arrangement of atoms) state having a relatively high resistivity. Conversely, applying a low current pulse to the amorphous state of the phase change material **106** for a long time may switch or change the phase change material **106** to the crystalline state. The phase change material **106** may also be capable of changing phases to switch between a first amorphous state and a second amorphous state, or between a first crystalline state and a second crystalline state.

By way of non-limiting example, the phase change material **106** may be a chalcogenide compound. As used herein, the term “chalcogenide compound” refers to a binary or multinary compound that includes at least one chalcogen atom and a more electropositive element or radical. As used herein, the term “chalcogen” refers to an element of Group VI of the Periodic Table, such as oxygen (O), sulfur (S), selenium (Se), or tellurium (Te). The electropositive element may include, but is not limited to, nitrogen (N), silicon (Si), nickel (Ni), gallium (Ga), germanium (Ge), arsenic (As), silver (Ag), indium (In), tin (Sn), antimony (Sb), gold (Au), lead (Pb), bismuth (Bi), or combinations thereof. The chalcogenide compound may be a binary, ternary, or quaternary alloy. Non-limiting examples of chalcogenide compounds suitable for use as the phase change material **106** include Sb and Te compounds, such as Sb<sub>2</sub>Te<sub>3</sub>; Ge and Te compounds, such as GeTe; In and Se compounds, such as In<sub>2</sub>Se<sub>3</sub>; Sn and Te compounds, such as SnTe; Bi and Te compounds, such as Bi<sub>2</sub>Te<sub>3</sub>; Sb and Te compounds, such as SbTe, or Sb<sub>2</sub>Te<sub>3</sub>; Sn and Se compounds, such as SnSe; Ge and Se compounds, such as GeSe; Ga, Se, and Te compounds, such as GaSeTe; Ge, Sb, and Te compounds, such as Ge<sub>2</sub>Sb<sub>2</sub>Te<sub>5</sub>; Sn, Sb, and Te compounds, such as SnSb<sub>2</sub>Te<sub>4</sub>; Au, Ge, Sn, and Te compounds, such as Au<sub>25</sub>Ge<sub>4</sub>Sn<sub>11</sub>Te<sub>60</sub>; Au, In, Sb, and Te compounds, such as AgInSbTe; Ag and Se compounds, such as Ag<sub>2</sub>Se; In and Te compounds, such as InTe; and In, Sb, and Te

(IST) compounds, such as InSbTe. In at least some embodiments, the phase change material **106** is IST.

The phase change material **106** may be formed on the first nitrogenated carbon material **104**, if present, or the first electrode **102** if the first nitrogenated carbon material **104** is not present. The phase change material **106** may be formed using conventional techniques, such as PVD, CVD, or ALD, which are not described in detail herein.

The second nitrogenated carbon material **108** may be a non-stoichiometric compound including C atoms and N atoms. The second nitrogenated carbon material **108** may function as an electrode configured to conduct current to the threshold switching material **110**. The second nitrogenated carbon material **108** may have an atomic percentage of nitrogen within a range of from about 0.10 atomic percent nitrogen to about 20 atomic percent nitrogen, such as from about 0.5 atomic percent nitrogen to about 10 atomic percent nitrogen. If the first nitrogenated carbon material **104** is present in the phase change memory cell **100**, the amount of nitrogen in the second nitrogenated carbon material **108** may be greater than, less than, or equal to the atomic percentage of nitrogen in the first nitrogenated carbon material **104**.

The second nitrogenated carbon material **108** may have a uniform nitrogen concentration profile or a non-uniform nitrogen concentration profile (e.g., stepwise, continuous, or a combination thereof). If the first nitrogenated carbon material **104** is present, the nitrogen concentration profile of the second nitrogenated carbon material **108** may be substantially the same as or may be different than the nitrogen concentration profile of the first nitrogenated carbon material **104**. By way of non-limiting example, the first nitrogenated carbon material **104** may have a uniform nitrogen concentration profile and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile; the first nitrogenated carbon material **104** may have a non-uniform nitrogen concentration profile and the second nitrogenated carbon material **108** may have a uniform nitrogen concentration profile; the first nitrogenated carbon material **104** may have a non-uniform nitrogen concentration profile that is varied stepwise and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied continuously; the first nitrogenated carbon material **104** may have a non-uniform nitrogen concentration profile that is varied continuously and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied stepwise; the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** may each have a non-uniform nitrogen concentration profile that is varied stepwise in a substantially similar or different manner; or the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** may each have a non-uniform nitrogen concentration profile that is varied continuously in a substantially similar or different manner.

Similar to the first nitrogenated carbon material **104** previously described, a thickness of the second nitrogenated carbon material **108** may be selected at least partially based on material characteristics of at least one other component of the phase change memory cell **100**. The thickness of the second nitrogenated carbon material **108** may be within a range of from about 100 Å to about 2000 Å, such as from about 300 Å to about 1500 Å. In at least some embodiments, the thickness of the second nitrogenated carbon material **108** is about 1000 Å. The thickness of the second nitrogenated carbon material **108** may be greater than, less than, or equal to the thickness of the first nitrogenated carbon material **104** (if present).

The second nitrogenated carbon material **108** may be formed on the phase change material **106** in a manner substantially similar to that described above with respect to forming the first nitrogenated carbon material **104** on the first electrode **102**.

The threshold switching material **110** may be any known material capable of being reversibly electrically switched (i.e., configured to reversibly electrically switch or change) from a relatively resistive state to a relatively conductive state and having substantially no tendency to undergo a structural or phase change under normal operating conditions of the phase change memory cell **100**. For example, subjecting the threshold switching material **110** to a voltage above a critical threshold level may switch or change the threshold switching material **110** from the relatively resistive state to the relatively conductive state. The relatively conductive state may continue until a current passing through the threshold switching material **110** drops below a critical holding level, at which time the threshold switching material **110** may switch or change to the relatively resistive state.

By way of non-limiting example, the threshold switching material **110** may be a chalcogenide compound including a chalcogen and an electropositive element. The chalcogen may be at least one of O, S, Se, Te, or Po. The electropositive element may include, but is not limited to, N, Si, Ni, Ga, Ge, As, Ag, In, Cd, Zn, Sn, Sb, Au, Pb, Bi, or combinations thereof. The chalcogenide compound may be a binary, ternary, or quaternary alloy. Non-limiting examples of chalcogenide compounds suitable for use as the threshold switching material **110** include As and Te compounds, such as As<sub>2</sub>Te<sub>3</sub>; As and Se compounds, such as As<sub>2</sub>Se<sub>3</sub>; As, Te, and Ge compounds, such as As<sub>30</sub>Te<sub>45</sub>Ge<sub>25</sub>; As, Se, and Ge compounds, such as As<sub>28</sub>Se<sub>42</sub>Ge<sub>30</sub>; As, S, Se, and Ge compounds, such as As<sub>30</sub>Si<sub>2</sub>Se<sub>33</sub>Ge<sub>25</sub>; and As, Te, Ge, Si, In compounds, such as As<sub>37</sub>Te<sub>39</sub>Ge<sub>9</sub>Si<sub>14</sub>In. In at least some embodiments, the threshold switching material **110** is As<sub>37</sub>Te<sub>39</sub>Ge<sub>9</sub>Si<sub>14</sub>In.

The threshold switching material **110** may be formed on the second nitrogenated carbon material **108** using conventional techniques, such as PVD, CVD, or ALD, which are not described in detail herein.

The third nitrogenated carbon material **112** may be a non-stoichiometric compound including C atoms and N atoms. The third nitrogenated carbon material **112** may function as an electrode configured to conduct current to the second electrode **114**. The third nitrogenated carbon material **112** may have an atomic percentage of nitrogen within a range of from about 0.10 atomic percent nitrogen to about 20 atomic percent nitrogen, such as from about 0.5 atomic percent nitrogen to about 10 atomic percent nitrogen. The amount of nitrogen in the third nitrogenated carbon material **112** may be greater than, less than, or equal to the atomic percentage of nitrogen in each of the first nitrogenated carbon material **104** (if present) and the second nitrogenated carbon material **108**.

The third nitrogenated carbon material **112** may have a uniform nitrogen concentration profile or a non-uniform nitrogen concentration profile (e.g., stepwise, continuous, or a combination thereof). The nitrogen concentration profile of the third nitrogenated carbon material **112** may be the substantially the same as or may be different than the nitrogen concentration profile of each of the first nitrogenated carbon material **104** (if present) and the second nitrogenated carbon material **108**. By way of non-limiting example, at least one of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** may have a uniform nitrogen concentration profile and the third nitrogenated carbon material **112** may have a non-uniform nitrogen concentration profile; at least one of the first nitrogenated carbon material

**104** and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile and the third nitrogenated carbon material **112** may have a uniform nitrogen concentration profile; at least one of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied stepwise and the third nitrogenated carbon material **112** may have a non-uniform nitrogen concentration profile that is varied continuously; at least one of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied continuously and the third nitrogenated carbon material **112** may have a non-uniform nitrogen concentration profile that is varied stepwise; the third nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied stepwise in a manner substantially similar to or different than that of at least one of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108**; or the third nitrogenated carbon material **108** may have a non-uniform nitrogen concentration profile that is varied continuously in a manner substantially similar to or different than that of at least one of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108**.

Similar to each of the first nitrogenated carbon material **104** and the second nitrogenated carbon material **108** previously described, a thickness of the third nitrogenated carbon material **112** may be selected at least partially based on material characteristics of one or more other components of the phase change memory cell **100**. The thickness of the third nitrogenated carbon material **112** may be within a range of from about 100 Å to about 2000 Å, such as about 300 Å to about 1500 Å. In at least some embodiments, the thickness of the third nitrogenated carbon material **112** is about 1000 Å. The thickness of the third nitrogenated carbon material **112** may be greater than, less than, or equal to the thickness of each of the first nitrogenated carbon material **104** (if present) and the second nitrogenated carbon material **108**.

The third nitrogenated carbon material **112** may be formed on the threshold switching material **110** in a manner substantially similar to that described above with respect to forming the first nitrogenated carbon material **104** on the first electrode **102**.

The second electrode **114** may include any suitable conductive material including, but not limited to, a metal, a metal alloy, a conductive metal oxide, or combinations thereof. By way of non-limiting example, the second electrode **114** may be formed of W, WN, Ni, TaN, Pt, Au, TiN, TiSiN, TiAlN, or MoN. The second electrode **114** may be formed of substantially the same material as the first electrode **102** or may be a different material than the first electrode **102**. In at least some embodiments, the second electrode **114** is formed from W. The second electrode **114** may be formed on the third nitrogenated carbon material **112** using conventional techniques, such as PVD, CVD, or ALD, which are not described in detail herein.

In further embodiments, relative positions of the phase change material **106** and the threshold switching material **110** may be different than described above. For example, as illustrated in FIG. 2, a phase change memory cell **100'** may include each component of the phase change memory cell **100** (FIG. 1) previously described (i.e., the optional first nitrogenated carbon material **104**, a phase change material **106'**, the second nitrogenated carbon material **108**, a threshold switching material **110'**, and the third nitrogenated carbon material **112**), except that the relative positions of the phase change material **106'** and the threshold switching material **110'** may

be switched or reversed. The first nitrogenated carbon material **104** may, optionally, be formed on the first electrode **102**, the threshold switching material **110'** may be formed on the first nitrogenated carbon material **104** (if present), the second nitrogenated carbon material **108** may be formed on the threshold switching material **110'**, the phase change material **106'** may be formed on the second nitrogenated carbon material **108**, the third nitrogenated carbon material **112** may be formed on the phase change material **106'**, and the second electrode **114** may be formed on the third nitrogenated carbon material **112**. Other than the described difference in the relative positions of the phase change material **106'** and the threshold switching material **110'**, each component of the phase change memory cell **100'** may be formed in a manner substantially similar to that described above with respect to each corresponding component of the phase change memory cell **100** (FIG. 1).

An embodiment of a phase change memory cell is disclosed. The phase change memory cell comprises a first chalcogenide compound on a first electrode, a first nitrogenated carbon material directly on the first chalcogenide compound, a second chalcogenide compound directly on the first nitrogenated carbon material, and a second nitrogenated carbon material directly on the second chalcogenide compound and directly on a second electrode.

A method of forming a phase change memory cell is also disclosed. The method comprises forming a first chalcogenide compound on a first electrode, forming a first nitrogenated carbon material directly on the first chalcogenide compound, forming a second chalcogenide compound on the first nitrogenated carbon material, and forming a second nitrogenated carbon material directly on the second chalcogenide compound.

Another embodiment of the present disclosure will now be described with reference to FIG. 3, which illustrates a phase change memory cell **200** including an optional first carbon material **204**, an optional first nitrogenated carbon material **206**, a phase change material **208**, a second nitrogenated carbon material **210**, a second carbon material **212**, a third nitrogenated carbon material **214**, a threshold switching material **216**, a fourth nitrogenated carbon material **218**, and a third carbon material **220**. As used herein, the term "carbon material" means and includes a material including carbon atoms but lacking nitrogen atoms. The term "carbon material" is used in contrast to the term "nitrogenated carbon material" in which both carbon atoms and nitrogen atoms are present. The nitrogenated carbon material may include trace amounts of additional elements, such as oxygen, hydrogen, or various metals. These elements may be present in small amounts, such as in impurity concentrations. The phase change memory cell **200** may be coupled to a first electrode **202** and a second electrode **222**. The first carbon material **204** may, optionally, be formed on the first electrode **202**, the first nitrogenated carbon material **206** may be formed on the first carbon material **204** (if present), the phase change material **208** may be formed on the first nitrogenated carbon material **206** (if present), the second nitrogenated carbon material **210** may be formed on the phase change material **208**, the second carbon material **212** may be formed on the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214** may be formed on the second carbon material **212**, the threshold switching material **216** may be formed on the third nitrogenated carbon material **214**, the fourth nitrogenated carbon material **218** may be formed on the threshold switching material **216**, the third carbon material **220** may be

formed on the fourth nitrogenated carbon material **218**, and the second electrode **222** may be formed on the third carbon material **220**.

The first carbon material **204**, if present, may include a plurality of carbon atoms. The first carbon material **204** is configured to conduct current to the phase change material **208**. A thickness of the first carbon material **204** may be selected at least partially based on material characteristics of at least one other component of the phase change memory cell **200** (e.g., electrical resistance of one or more of the first nitrogenated carbon material **206**, the phase change material **208**, the second nitrogenated carbon material **210**, the second carbon material **212**, the third nitrogenated carbon material **214**, and the threshold switching material **216**). The thickness of the first carbon material **204** may be within a range of from about 100 Å to about 2000 Å, such as about 300 Å to about 1500 Å. The first carbon material **204** may be formed on the first electrode **202** using conventional techniques, such as PVD, CVD, or ALD, which are not described in detail herein. The first electrode **202** may be substantially similar to and may be formed in a substantially similar manner as the first electrode **102** described above.

The first nitrogenated carbon material **206** may be substantially similar to the first nitrogenated carbon material **104** previously described, except that the first nitrogenated carbon material **206** may have a reduced thickness compared to the thickness of the first nitrogenated carbon material **104** described above. The thickness of the first nitrogenated carbon material **206** may be within a range of from about 5 Å to about 100 Å, such as from about 5 Å to about 50 Å, or from about 5 Å to about 25 Å. The first nitrogenated carbon material **206** may function as an adhesion material to bind or adhere the first carbon material **204** to the phase change material **208**. The first nitrogenated carbon material **206** may provide increased adhesion strength between the first carbon material **204** and the phase change material **208** relative to forming the phase change material **208** directly on the first carbon material **204**, reducing a risk of delamination. The adhesion strength between the first carbon material **204** and the phase change material **208** may be measured by the fracture energy sufficient to cause an adhesion failure between first carbon material **204** and the phase change material **208**. The adhesion strength may be determined in a four point bend test, as known in the art. A high adhesion strength corresponds to a high fracture energy sufficient to cause the adhesion failure, or delamination, of the first carbon material **204** and the phase change material **208**. The first nitrogenated carbon material **206** may be formed on the first carbon material **204**, if present, in a manner substantially similar to that previously described with respect to forming the first nitrogenated carbon material **104** on the first electrode **102**. Optionally, the first carbon material **204** and the first nitrogenated carbon material **206** may be formed in sequentially through a controlled introduction of nitrogen. For example, within a deposition chamber (e.g., a PVD chamber, as described above), a flow of nitrogen gas may initially be withheld to form of the first carbon material **204**, and may be subsequently enabled to form the first nitrogenated carbon material **206** on the first carbon material **204**. If the first carbon material **204** is not present, the first nitrogenated carbon material **206** may be omitted.

The phase change material **208**, the threshold switching material **216**, and the second electrode **222** may be substantially similar to and may be formed in a substantially similar manner as the phase change material **106**, the threshold switching material **110**, and the second electrode **114** described above, respectively.

Each of the second carbon material **212** and the third carbon material **220** may include a plurality of carbon atoms. The second carbon material **212** and the third carbon material **220** conduct current to the threshold switching material **216** and the second electrode **222**, respectively. Similar to the first carbon material **204** described above, a thickness of each of the second carbon material **212** and the third carbon material **220** may be selected based on material characteristics of at least one other component of the phase change memory cell **200**. The thickness of each of the second carbon material **212** and the third carbon material **220** may be within a range of from about 100 Å to about 2000 Å, such as from about 300 Å to about 1500 Å. The thickness of at least one of the first carbon material **204** (if present), the second carbon material **212**, and the third carbon material **220** may be substantially the same as the thickness of at least one other of the first carbon material **204** (if present), the second carbon material **212**, and the third carbon material **220**. Conversely, the thickness of each of the first carbon material **204** (if present), the second carbon material **212**, and the third carbon material **220** may be different. Each of the second carbon material **212** and the third carbon material **220** may be formed using conventional techniques, such as PVD, CVD, or ALD, which are not described in detail herein.

Each of the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218** may be substantially similar to the first nitrogenated carbon material **104** previously described, except that each may have a reduced thickness as compared to the thickness of the first nitrogenated carbon material **104**. The second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218** may function as an adhesion material in a manner substantially similar to that described above for the first nitrogenated carbon material **104**. The thickness of each of the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material may be within a range of from about 5 Å to about 100 Å, such as from about 5 Å to about 50 Å, or from about 5 Å to about 25 Å. The thickness of at least one of the first nitrogenated carbon material **206** (if present), the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218** may be substantially the same as the thickness of at least one other of the first nitrogenated carbon material **206** (if present), the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218**. Conversely, the thicknesses of each of the first nitrogenated carbon material **206** (if present), the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218** may be different from one another. Each of the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitrogenated carbon material **218** may impart increased adhesion strength to the phase change memory cell **200** relative to directly joining or bonding **18** components of the phase change memory cell **200** adjacent opposing sides of each nitrogenated carbon material (e.g., forming the second carbon material **212** directly on the phase change material **208**, forming the threshold switching material **216** on the second carbon material **212**, and forming the third carbon material on the threshold switching material **216**). The method of forming each of the first nitrogenated carbon material **206**, the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214**, and the fourth nitro-



generated carbon material **218** may be substantially similar to that previously described with respect to the first nitrogenated carbon material **206**.

In yet further embodiments, relative positions of a phase change material **208'** and a threshold switching material **216'** may be different than described above in FIG. 3. For example, as illustrated in FIG. 4, a phase change memory cell **200'** may include each component of the phase change memory cell **200** (FIG. 3) previously described (i.e., the optional first carbon material **204**, the optional first nitrogenated carbon material **206**, the phase change material **208'**, the second nitrogenated carbon material **210**, the second carbon material **212**, the third nitrogenated carbon material **214**, the threshold switching material **216'**, the fourth nitrogenated carbon material **218**, and the third carbon material **220**), except that the relative positions of the phase change material **208** and the threshold switching material **216** may be switched or reversed. The first carbon material **204** may, optionally, be formed on the first electrode **202**, the first nitrogenated carbon material **206** may be formed on the first carbon material **204** (if present), the threshold switching material **216'** may be formed on the first nitrogenated carbon material **206** (if present), the second nitrogenated carbon material **210** may be formed on the threshold switching material **216'**, the second carbon material **212** may be formed on the second nitrogenated carbon material **210**, the third nitrogenated carbon material **214** may be formed on the second carbon material **212**, the phase change material **208'** may be formed on the third nitrogenated carbon material **214**, the fourth nitrogenated carbon material **218** may be formed on the phase change material **208'**, the third carbon material **220** may be formed on the fourth nitrogenated carbon material **218**, and the second electrode **222** may be formed on the third carbon material **220**. Other than the described difference in the relative positions of the phase change material **208'** and the threshold switching material **216'**, each component of the phase change memory cell **200'** may be formed in a manner substantially similar to that described above with respect to each corresponding component of the phase change memory cell **200** (FIG. 3).

Another embodiment of a phase change memory cell is disclosed. The phase change memory cell comprises a first chalcogenide compound on a first electrode, a first nitrogenated carbon material directly on the first chalcogenide compound, a first carbon material directly on the first nitrogenated carbon material, a second nitrogenated carbon material directly on the first carbon material, a second chalcogenide compound directly on the second nitrogenated carbon material, a third nitrogenated carbon material directly on the second chalcogenide compound, and a second carbon material directly on the third nitrogenated carbon material and directly on a second electrode.

FIG. 5 illustrates an embodiment of a phase change memory array **300** including a plurality of the phase change memory cells **304**. The phase change memory cells **304** may be one of the phase change memory cells **100**, **100'**, **200**, **200'** previously described. The plurality of the phase change memory cells **304** may be positioned between a plurality of word lines **302** and a plurality of digit lines **306**. The plurality of word lines **302** may correspond to one of the first electrodes **102**, **202** previously described. The plurality of digit lines **306** may correspond to one of the second electrodes **114**, **222** previously described. The relative positions of the plurality of word lines **302** and the plurality of digit lines **306** illustrated in FIG. 5 may be switched where an arrangement of the materials of the phase change memory cells **304** is modified accordingly. Each of the word lines **302** may extend in a first

direction and may connect a row of the phase change memory cells **304**. Each of the digit lines **306** may extend in a second direction and may connect a column of the phase change memory cells **304**. Each phase change memory cell **304** may include a word line node (not shown) coupled to a respective word line **302**, and a digit line node (not shown) coupled to a respective digit line **306**. A voltage applied to the word lines **302** and digit lines **306** may be controlled such that an electric field may be selectively applied to at least one word line **302** and to at least one digit line **306**, enabling the phase change memory cells **304** to be selectively operated. Accordingly, a phase change memory device may be formed which includes a phase change memory array **300**.

FIG. 6 illustrates a phase change memory device **400** in accordance with an embodiment of the present disclosure. The phase change memory device **400** may include the phase change memory array **300** (FIG. 5) including the plurality of phase change memory cells **304**, the plurality of word lines **302**, the plurality of digit lines **306**, an insulator material **308**, a first dielectric material **310**, and an optional second dielectric material **312**. Each of the insulator material **308**, the first dielectric material **310**, and the optional second dielectric material **312** may be a suitable insulative or dielectric material known in the art including, but not limited to, silicon oxide, silicon nitride, silicon oxynitride, a spin-on-glass (SOG), a phosphosilicate glass (PSG), tetraethyl orthosilicate (TEOS), or borophosphosilicate glass (BPSG). The phase change memory device **400** may be formed by conventional techniques.

An embodiment of a phase change memory device is also disclosed. The phase change memory device comprises a plurality of word lines, a plurality of digit lines perpendicular to the plurality of word lines, and a plurality of phase change memory cells arranged in an array of rows and columns. Each phase change memory cell of the plurality of phase change memory cells is coupled to a respective word line of the plurality of word lines and coupled to a respective digit line of the plurality of digit lines. Each phase change memory cell comprises a first chalcogenide compound, a first nitrogenated carbon material directly on the first chalcogenide compound, a second chalcogenide compound on the first nitrogenated carbon material, and a second nitrogenated carbon material directly on the second chalcogenide compound.

By way of non-limiting example and as illustrated in FIG. 7A, the plurality of word lines **302** may be formed in the insulator material **308** using conventional techniques, which are not described in detail herein. As shown in FIG. 7B, a phase change memory cell **304'** may be formed on the plurality of word lines **302** and insulator material **308** in a manner substantially similar to that previously described for one of the phase change memory cells **100**, **100'**, **200**, **200'**. As illustrated in FIG. 7C, a plurality of openings **315** may be formed in a hardmask **314** overlying the phase change memory cell **304'**. The openings **315** may be used as a mask to transfer a corresponding pattern into the phase change memory cell **304'** to form the plurality of phase change memory cells **304** and openings **315'**, as depicted in FIG. 7D. Remaining portions of the hardmask **314** may be removed (e.g., by etching or chemical mechanical planarization), the first dielectric material **310** may optionally be formed over the plurality of phase change memory cells **304**, the plurality of openings **315'** may be filled with the dielectric material **312**, and a portion of at least one of the first dielectric material **310** (if present), the second dielectric material **312**, and the plurality of phase change memory cells **304** may be removed (e.g., by chemical mechanical planarization) to form a substantially planar sur-

15

face **318**, as depicted in FIG. 7E. The plurality of digit lines **306** may then be formed on the substantially planar surface **318** using conventional techniques to form the phase change memory device **400** illustrated in FIG. 6.

In use and operation, the word lines **302** and the digit lines **306** of the phase change memory device **400** are connected to circuitry (not shown) configured to program and read the phase change memory device **400**. Current delivered to the plurality of word lines **302** (e.g., by electrical contact with an interconnect) may flow through the plurality of phase change memory cells **304**, and to the plurality of digit lines **306**. By way of non-limiting example and referring to FIG. 1, if the plurality of phase change memory cells **304** (FIG. 6) are the phase change memory cells **100** described above, current from the plurality of word lines **302** (FIG. 6) may flow through the optional first nitrogenated carbon material **104**, the phase change material **106**, the second nitrogenated carbon material **104**, the threshold switching material **110**, and the third nitrogenated carbon material **112**, to the digit lines **306** (FIG. 6). As the current passes through the phase change material **106**, at least one detectable property change (e.g., an electrical resistivity change, as described above) may occur and be utilized to distinguish logic values of the phase change memory cell **100** as desired.

The phase change memory cells **100**, **100'**, **200**, **200'** and phase change memory device **400** of the present disclosure advantageously reduce energy demands, increase memory lifespan, and decrease performance degradation issues as compared to conventional phase change memory cells and devices. For example, the nitrogenated carbon materials included in the phase change memory cells **100**, **100'**, **200**, **200'** and phase change memory device **400** described above provide increased resistivity relative to conventional electrodes, enabling the generation of more heat for the phase change material and reducing energy consumption. The nitrogenated carbon materials also exhibit increased adhesion strength, improved resistivity stability, increased surface smoothness, and decreased reactivity as compared to conventional electrodes (e.g., carbon, TiN), facilitating enhanced durability and improved reliability. Providing the nitrogenated carbon materials on opposing sides of at least the phase change material of the phase change memory cells **100**, **100'**, **200**, **200'** may also increase heat retention within the phase change material, resulting in relatively improved data retention characteristics.

The following example serves to explain embodiments of the present disclosure in more detail. The example is not to be construed as being exhaustive or exclusive as to the scope of the disclosure.

## EXAMPLES

### Example 1

A graphical representation of the resistivity stability of a nitrogenated carbon material at different annealing temperatures relative to a carbon material at different annealing temperatures is shown in FIG. 8. A nitrogenated carbon material containing 5 atomic percent nitrogen was sputtered on silicon oxide substrates (8 inch wafers including 100 nm of oxide) to a thickness of 1000 Å. A carbon material was sputtered on silicon oxide substrates (8 inch wafers including 100 nm of oxide) to a thickness of 500 Å. The samples were segmented, and resistivity of the nitrogenated carbon material and the carbon material was measured using the Van der Pauw four-point probe methodology. In FIG. 8, the x-axis refers to an annealing temperature (° C.), and the y-axis refers to a resistivity ( $\Omega\text{cm}$ ).

16

As depicted in FIG. 8, across three separate heating cycles sequentially tested (i.e., ambient temperature  $\rightarrow$  400° C.  $\rightarrow$  ambient temperature; ambient temperature  $\rightarrow$  500° C.  $\rightarrow$  ambient temperature; and ambient temperature  $\rightarrow$  600° C.  $\rightarrow$  ambient temperature), the initial resistivity and the final resistivity of the nitrogenated carbon material (represented by the solid lines) was more reproducible than the initial resistivity and the final resistivity of the carbon material (represented by the dashed lines). In addition, the resistivity of the nitrogenated carbon materials was found to be substantially independent of the thermal history of the nitrogenated carbon material, and no hysteresis or degradation of the nitrogenated carbon materials was observed.

While the present disclosure is susceptible to various modifications and alternative forms, specific embodiments have been shown by way of example in the drawings and have been described in detail herein. However, the present disclosure is not intended to be limited to the particular forms disclosed. Rather, the present disclosure is to cover all modifications, equivalents, and alternatives falling within the scope of the present disclosure as defined by the following appended claims and their legal equivalents.

What is claimed is:

1. A phase change memory cell, comprising:
  - a first chalcogenide compound on a first electrode;
  - a first nitrogenated carbon electrode directly on the first chalcogenide compound;
  - a second chalcogenide compound directly on the first nitrogenated carbon electrode; and
  - a second nitrogenated carbon electrode exhibiting a different thickness than the first nitrogenated carbon electrode that is located directly on each of the second chalcogenide compound and a second electrode, the second nitrogenated carbon electrode and the first nitrogenated carbon electrode each independently comprising carbon at greater than or equal to about 80 atomic percent and nitrogen at less than or equal to about 20 atomic percent.
2. The phase change memory cell of claim 1, further comprising a third nitrogenated carbon electrode directly on the first electrode and directly on the first chalcogenide compound.
3. The phase change memory cell of claim 1, wherein the first chalcogenide compound comprises a phase change material, and wherein the second chalcogenide compound comprises a threshold switching material.
4. The phase change memory cell of claim 1, wherein the first chalcogenide compound comprises a threshold switching material, and wherein the second chalcogenide compound comprises a phase change material.
5. The phase change memory cell of claim 1, wherein each of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode independently comprises carbon at greater than or equal to about 90 percent and nitrogen at less than or equal to about 10 atomic percent.
6. The phase change memory cell of claim 1, wherein an atomic percentage of nitrogen in the first nitrogenated carbon electrode is different than an atomic percentage of nitrogen in the second nitrogenated carbon electrode.
7. The phase change memory cell of claim 1, wherein an atomic percentage of nitrogen in the first nitrogenated carbon electrode is the same as an atomic percentage of nitrogen in the second nitrogenated carbon electrode.
8. The phase change memory cell of claim 1, wherein a thickness of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode is within a range of from about 100 Å to about 2000 Å.

17

9. The phase change memory cell of claim 1, wherein at least one of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode comprises a uniform nitrogen concentration profile.

10. The phase change memory cell of claim 1, wherein at least one of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode comprises a non-uniform nitrogen concentration profile.

11. The phase change memory cell of claim 10, wherein the non-uniform nitrogen concentration profile varies continuously across a thickness of the at least one of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode.

12. The phase change memory cell of claim 10, wherein the non-uniform nitrogen concentration profile varies stepwise across a thickness of the at least one of the first nitrogenated carbon electrode and the second nitrogenated carbon electrode.

13. A method of forming a phase change memory cell, comprising:

forming a first chalcogenide compound on a first electrode; forming a first nitrogenated carbon electrode directly on the first chalcogenide compound;

forming a second chalcogenide compound directly on the first nitrogenated carbon electrode;

forming a second nitrogenated carbon electrode exhibiting a different thickness than the first nitrogenated carbon electrode directly on the second chalcogenide compound; and forming a second electrode directly on the second nitrogenated carbon electrode, wherein the second nitrogenated carbon electrode and the first nitrogenated carbon electrode each independently comprises carbon at greater than or equal to about 80 atomic percent and nitrogen at less than or equal to about 20 atomic percent.

14. The method of claim 13, further comprising forming a third nitrogenated carbon electrode comprising carbon and nitrogen between the first electrode and the first chalcogenide compound.

15. A phase change memory device, comprising:

a plurality of word lines;

a plurality of digit lines perpendicular to the plurality of word lines; and

a plurality of phase change memory cells arranged in an array of rows and columns, each phase change memory cell of the plurality of phase change memory cells

18

coupled to a respective word line of the plurality of word lines and coupled to a respective digit line of the plurality of digit lines and comprising:

a first chalcogenide compound;

a first nitrogenated carbon electrode directly on the first chalcogenide compound;

a second chalcogenide compound directly on the first nitrogenated carbon electrode; and

a second nitrogenated carbon electrode exhibiting a different thickness than the first nitrogenated carbon electrode that is located directly on the second chalcogenide compound, the second nitrogenated carbon electrode and the first nitrogenated carbon electrode each independently comprising carbon at greater than or equal to about 80 atomic percent and nitrogen at less than or equal to about 20 atomic percent.

16. The phase change memory cell of claim 1, wherein the first nitrogenated carbon electrode and the second nitrogenated carbon electrode consist of carbon and nitrogen.

17. The phase change memory cell of claim 1, wherein the first nitrogenated carbon electrode and the second nitrogenated carbon electrode are crystalline.

18. The phase change memory cell of claim 1, wherein the first nitrogenated carbon electrode exhibits a different amount of nitrogen than the second nitrogenated carbon electrode.

19. The phase change memory cell of claim 1, wherein the first nitrogenated carbon electrode exhibits a different nitrogen concentration profile than the second nitrogenated carbon electrode.

20. The phase change memory cell of claim 1, wherein the first chalcogenide compound comprises at least one of  $\text{Sb}_2\text{Te}_3$ ,  $\text{GeTe}$ ,  $\text{In}_2\text{Se}_3$ ,  $\text{SnTe}$ ,  $\text{Bi}_2\text{Te}_3$ ,  $\text{SbTe}$ ,  $\text{Sb}_2\text{Te}_3$ ,  $\text{SnSe}$ ,  $\text{GeSe}$ ,  $\text{GaSeTe}$ ,  $\text{Ge}_2\text{Sb}_2\text{Te}_5$ ,  $\text{SnSb}_2\text{Te}_4$ ,  $\text{Au}_{25}\text{Ge}_4\text{Sn}_{11}\text{Te}_{60}$ ,  $\text{AgInSbTe}$ ,  $\text{Ag}_2\text{Se}$ ,  $\text{InTe}$ , and  $\text{InSbTe}$ .

21. The phase change memory cell of claim 1, wherein the first chalcogenide compound comprises In, Sb, and Te.

22. The phase change memory cell of claim 1, wherein the second chalcogenide compound comprises at least one of  $\text{As}_2\text{Te}_3$ ,  $\text{As}_2\text{Se}_3$ ,  $\text{As}_{30}\text{Te}_{45}\text{Ge}_{25}$ ,  $\text{As}_{28}\text{Se}_{42}\text{Ge}_{30}$ ,  $\text{As}_{30}\text{S}_{12}\text{Se}_{33}\text{Ge}_{25}$ , and  $\text{As}_{37}\text{Te}_{39}\text{Ge}_9\text{Si}_{14}\text{In}$ .

23. The phase change memory cell of claim 1, wherein the second chalcogenide compound comprises As, Te, Ge, Si, and In.

\* \* \* \* \*